

ALPHEX HV (HVLP 68)

HVLP Hydraulic Oil according DIN 51524, part 3

Description:

ALPHEX HV (HVLP 68) is a mineral high-performance hydraulic oil with very good viscosity temperature behaviour applicable for high pressure hydraulic systems being exposed to changing temperatures.

Characteristics

- High viscosity index
- High pressure susceptibility
- Reliable wear protection
- Oxidation protection properties
- Reliable protection against corrosion
- Excellent air separating ability
- No foaming formation
- High ageing stability
- Neutral towards sealing materials
- Resistant to water
- Good filtration

Usable for

DIN 51524/3 HVLP 68	ISO VG-68
ISO	11158
AFNOR	NFE 48-603 (HM, HV)
ASTM	D6158
SAE	MS 1004
We recommend this product for:	
AIST	127, 136
ASLE	70-1/70-2/70-3
BOSCH	Rexroth
CETOP	RP 91 H (HM, HV)
DAVID BROWN	ET 19, ET 33
DENISON	TP 02100
EATON VICKERS	M 2950-S, I-286-S
FZG-Test	A8, 3/90 12th damage loading step
GM	LS 2
HOESCH	HWN 2333
JCMAS	P041 HK
SEB	181222
SIS	SS 155434
US STEEL	126-127
VDMA	24318

Disposal:

- **ALPHEX HV (HVLP 68)** is assigned to category 2 of used oils and thus is free for disposal.

Miscibility:

- **ALPHEX HV (HVLP 68)** Hydraulic oil of HVLP-range is fully compatible to comparable lubrications and can be mixed without any doubts. However, it is recommendable to refill **ALPHEX HV (HVLP 68)** Hydraulic Oil of HVLP-range only.

Effects

- Extremely high operating reliability of hydraulic system
- Favourable operating properties
- Highest standard performance
- Low freezing point
- Reduction of kinds
- No seasonal suspended change necessary
- Increased total efficiency

Utilization

- Predominantly hydraulic systems operating in the open according to DIN 51524
- such as mobile hydraulic systems, hydraulic lifts, skids, wheel tractor, hydraulic excavator, construction equipment etc.

ALPHEX HV (HVLV 68)

Article No.	Packaging unit	
STL 1040 825	Can	20 L
STL 1040 826	Drum	60 L
STL 1040 828	Drum	200 L
STL 1440 829	PE-Container	1000 L

Typical characteristics:

Specific weight at 15°C	kg/m ³	870
Viscosity at 40°C	mm ² /s	66,2
Viscosity at 100°C	mm ² /s	10,9
Viscosity index		151
Flash point COC	°C	223
Pourpoint	°C	-30
TAN	mgKOH/g	-

